


Could you explain the information on a TP grade stamp?

Explanation for the Audited by TP grade stamp examples.


1 – 2 and 6 – 9 are the same for Exposure 1 and Exterior.



AUDITED BY
TP[®]

PS 1-09
EXPOSURE 1
SHEATHING SPAN RATED
19/32 CATEGORY
40/20
SIZED FOR SPACING
MILL NAME
MILL #
THICKNESS: 0.563

1. Audited by TP is the 3rd party certification agency.
2. PS1-09 is the standard.
3. EXPOSURE 1 - Glue bond durability and indicates that D veneer is used in the construction.
4. EXTERIOR – Glue bond durability. C grade is the minimum veneer in the construction.
5. C – C means there is a C grade face and a C grade back. Inner plies are C grade or better.
6. 19/32 CATEGORY - Thickness of panel.
7. 40 / 20 Span Rating The left number is the span rating for roof and the 20 is the span rating for floors or walls.
8. Mill name and Mill #.
9. THICKNESS: 0.563 California Weight and Measurement Requirements. Reference D1 of the PS1-09 Standard.



AUDITED BY
TP[®]

PS 1-09
EXTERIOR
SHEATHING SPAN RATED
C – C
19/32 CATEGORY
40/20
SIZED FOR SPACING
MILL NAME
MILL #
THICKNESS: 0.563

Sheathing Span Rated Panels, CD Sheathing Span Rated, and CC Sheathing Span Rated are interchangeable with other certification agencies. Reference the standard for sheathing product requirement and not the certification agency. Rated Sheathing (APA), Sheathing Span (TECO) and Sheathing Span Rated (TP).

